

## Purple Organic Fueled Star:

**Name:** Agten KClO<sub>3</sub>/Lactose purple

**Source:** Jeroen Agten

<b>Chemical</b>	<b>Parts by weight</b>
Potassium Chlorate	60
Lactose	20
Parlon	10
Copper Oxide, Black	6
Strontium Carbonate	4

### **Notes:**

Stars can be cut using acetone as a solvent for the Parlon.

Cut 9mm stars for a 3" shell, let them dry for 24 hours, and prime with a thin layer of black powder.

Stars can also be rolled, pressed or pumped using dextrin as a binder. Replace 25% of the lactose by dextrin and proceed as with any normal dextrin bound star.